

Test Method

■ Anti-Repulsion

Substrate: Top side- MG/PC(180 x 2 x 0.5mm(t)), Bottom side-Ink coated PMMA((180 x 20 x 2mm(t))

♦ Specimen Dimension : 180mm x 20mm


◆ Adhesion condition : 5kgf, 5sec


 \spadesuit Aging condition: 72hrs, RT \rightarrow 48hr at 50°C, 95% \rightarrow 1hr at RT \rightarrow 48hr at -20°C \rightarrow 1hr at RT

 \rightarrow 48hr at 80°C,85% \rightarrow 1hr at RT

Record : Repulsion height

♠ Requiement : 0 mm at RT, less than 5mm after above aging test







EG-401-04, Rev.0, A4 MAINEGCOM Co., Ltd.